



urecel





QUICKDRY

# FOAM SPECIFICATION DATA

ASTM D3574	<b>Density</b>	32 ± 3 kg/m <sup>3</sup>	2 ± 0.2 lbs/ft <sup>3</sup>	<h2>SUPER FIRM</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	220-260 N	49-58 lbf	
ASTM D3574	<b>65% ILD*</b>	396 - 832 N	89 - 187 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
	<b>COLOR</b>	Light Red	Light Red	

ASTM D3574	<b>Density</b>	31 ± 2 kg/m <sup>3</sup>	1.9 ± 0.1 lbs/ft <sup>3</sup>	<h2>FIRM</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	180-220 N	40-49 lbf	
ASTM D3574	<b>65% ILD*</b>	324-704 N	73 - 158 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
	<b>COLOR</b>	Light Orange	Orange	

ASTM D3574	<b>Density</b>	29 ± 2 kg/m <sup>3</sup>	1.8 ± 0.1 lbs/ft <sup>3</sup>	<h2>MEDIUM</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	145 - 180 N	33-40 lbf	
ASTM D3574	<b>65% ILD*</b>	261 - 576 N	59 - 130 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
	<b>COLOR</b>	Light Yellow	Light Yellow	


ASTM D3574	<b>Density</b>	27 ± 2 kg/m <sup>3</sup>	1.7 ± 0.1 lbs/ft <sup>3</sup>	<h2>SOFT</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	115-145 N	26-33 lbf	
ASTM D3574	<b>65% ILD*</b>	207-464 N	47 - 104 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
	<b>COLOR</b>	Light Green	Light Green	


urecel



QUICKDRY

# FOAM SPECIFICATION DATA


ASTM D3574	<b>Density</b>	26 ± 2 kg/m <sup>3</sup>	1.6 ± 0.1 lbs/ft <sup>3</sup>	<h2>SUPER SOFT</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	85-115 N	19-26 lbf	
ASTM D3574	<b>65% ILD*</b>	153-368 N	34-83 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
ASTM D3574	<b>COLOR</b>	Light Blue	Light Orange	


ASTM D3574	<b>Density</b>	27 ± 2 kg/m <sup>3</sup>	1.7 ± 0.1 lbs/ft <sup>3</sup>	<h2>EXTRA SUPER SOFT</h2> 
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	65-85 N	15 - 19 lbf	
ASTM D3574	<b>65% ILD*</b>	17 - 272 N	26 - 61 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.5 kg/cm <sup>2</sup>	> 7.1 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
ASTM D3574	<b>COLOR</b>	Light Purple	Royal Jelly	


# FOAM SPECIFICATION DATA



ASTM D3574	<b>Density</b>	35 ± 2 kg/m <sup>3</sup>	2.2 ± 0.1 lbs/ft <sup>3</sup>	<h2>SUPER FIRM</h2> 
ASTM D3574	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	220-260 N	49-58 lbf	
ASTM D3574	<b>65% ILD*</b>	396-832 N	89 - 187 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Red	Light Red	

ASTM D3574	<b>Density</b>	> 32 ± 2 kg/m <sup>3</sup>	> 2±0.1 lbs/ft <sup>3</sup>	<h2>FIRM</h2> 
ASTM D3574	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	180-220 N	40-49 lbf	
ASTM D3574	<b>65% ILD*</b>	324-704 N	73 - 158 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Orange	Orange	

ASTM D3574	<b>Density</b>	> 30 ± 2kg/m <sup>3</sup>	> 1.9±0.1 lbs/ft <sup>3</sup>	<h2>MEDIUM</h2> 
ASTM D3574	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	145-180 N	33-40 lbf	
ASTM D3574	<b>65% ILD*</b>	261-576 N	59 - 130 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Yellow	Light Yellow	

ASTM D3574	<b>Density</b>	> 28±2 kg/m <sup>3</sup>	> 1.75±0.1 lbs/ft <sup>3</sup>	<h2>SOFT</h2> 
ASTM D3574	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	115-145 N	26-33 lbf	
ASTM D3574	<b>65% ILD*</b>	207-464 N	47 - 104 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Green	Light Green	



# FOAM SPECIFICATION DATA



ASTM D3574	<b>Density</b>	> 26 ± 2 kg/m <sup>3</sup>	> 1.6 ± 0.1 lbs/ft <sup>3</sup>	<h2>SUPER SOFT</h2>
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	85-115 N	19-26 lbf	
ASTM D3574	<b>65% ILD*</b>	153-368 N	34-83 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.6 kg/cm <sup>2</sup>	> 8.5 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Blue	Light Orange	

ASTM D3574	<b>Density</b>	> 27 ± 2 kg/m <sup>3</sup>	> 1.7 ± 0.1 lbs/ft <sup>3</sup>	<h2>EXTRA SUPER SOFT</h2>
	<b>PPI Count</b>	20-30 cell/25mm	20-30 cell/in	
ASTM D3574	<b>Ball Rebound</b>	> 30 %	> 30 %	
ASTM D3574	<b>25% ILD*</b>	65-85 N	15 - 19 lbf	
ASTM D3574	<b>65% ILD*</b>	117-272 N	26 - 61 lbf	
ASTM D3575	<b>Support Factor</b>	1.8 -3.2	1.8 -3.2	
ASTM D3574	<b>Tensile Strength</b>	> 0.5 kg/cm <sup>2</sup>	> 7.1 psi	
ASTM D3574	<b>Elongation</b>	> 100 %	> 100 %	
ASTM D3574	<b>Tear Strength</b>	> 0.3 kg/cm	> 1.7 psi	
CS TB 117	<b>FR Class</b>	Pass	Pass	
	<b>COLOR</b>	Light Purple	Royal Jelly	